

HP Concrete Cold Patch

*The year-round
- All Season -
High Performance
Concrete Cold Patch*



The **FAST** Concrete Patch.

CRAFCOTM
INC
AN ERGONIS COMPANY

"Pavement Preservation Products"

Concrete Repair

RECOMMENDED INSTALLATION PROCEDURES

Crafcro HP Concrete Cold Patch is a unique, gray color, cold applied, single component patching material. Use **HP** to repair potholes, spalls, cracks and other confined voids and distresses over 1 inch wide and greater than ½ inch deep in Portland Cement concrete. It can also be used to repair roads, highways, streets, airport pavements, parking lots, bridge and parking decks, sidewalks, walkways and floors. Unlike most other concrete patching materials, no mixing, heating or special installation equipment is required.

INSTALLATION

- Sweep and blow the repair area of all loose debris before applying **HP**.
- The repair area surfaces can be damp but should not have free moisture present during installation.
- Remove **HP** and place from the bag into the prepared repair area.
- For best performance, **HP** should be applied at least ½ inch in thickness. For repairs from ½ inch to 2 inches thick, apply product in a single layer and compact. Repairs deeper than 2 inches should be filled in layers, from 1 to 2 inches thick, with compaction of each layer. The final layer should be placed approximately ¼ to ½ inch above the surface, and then be compacted to surface level with a hand or mechanical tamper or multiple passes from a vehicle tire.
- Following compaction, clean up any excess **HP** and open to traffic. If needed in warm climates, initial surface tack can be reduced with a light sprinkle application of Portland Cement, calcium carbonate powder, or fine sand over the compacted surface.

HP should be installed when pavement temperatures are between 30 and 100F. If applying when pavement temperatures are below 30°F, the repair area can be warmed to at least 30°F using a torch or heat lance. **HP Concrete Cold Patch** can be stored in a warmer area not exceeding 90°F prior to use to improve workability at colder temperatures.

STORAGE Pallets and bags of **HP** should be kept intact and stored under cover. Shelf life of properly stored product in unopened pallets and bags is up to one year. To maintain workability, leftover **HP Concrete Cold Patch** from an opened bag should be placed in an airtight container such as a pail or bucket with a tight fitting lid.



Quick facts:

- Works in all weather conditions: cold or hot.
- Easy to use bags prevent waste and saves money.
- No mixing, mechanical compaction or tacking.
- Cost effective with no messy clean-up or time constraints.
- Adheres to concrete.
- All season, use in summer or winter.
- One man operation.

50lb / 22.7kg bag usage guide		
Repair Area Size	Depth in inches	Quantity per Repair
6 in X 6 in	1"	0.05 bag
	2"	0.1 bag
	4"	0.2 bag
	6"	0.3 bag
12 in X 12 in	1"	0.2 bag
	2"	0.4 bag
	4"	0.8 bag
	6"	1.2 bag
24 in X 24 in	1"	0.8 bag
	2"	1.6 bag
	4"	3.2 bag
	6"	4.8 bag

WARNING

This product contains a chemical known to the state of California to cause cancer, birth defects, or other reproductive harm. (Proposition 65)

For more information on Crafcro products contact your local Crafcro Distributor or call:



www.crafcro.com
800-528-8242

420 N. Roosevelt Ave., Chandler, Arizona 85226 • Phone 1-602-276-0406 / Fax: 1-480-961-0513
INTERNATIONAL • Phone +1-602-276-0406 / Fax: +1-480-961-0513

Your local Crafcro Representative: